



NATIONAL STANDARD

National Standard, LLC

3602 N. Perkins Road

Stillwater, OK 74075

Product: **Tru-Core FC 70T**

Classification: **E70T-1M-H8, E70T-1C-H8, E70T-9M-H8, E70T-9C-H8, E492T-9-H8**

Specification: **AWS A5.20, ASME SFA 5.20, CSA W48-2014**

Test completion date: **November 22, 2016**

MO Number: **493-1MS**

Certificate of Conformance

This is to certify that the product named above and referenced on the sales invoice number is of the same classification, manufacturing process, and raw material requirements as the electrode which was used for the tests conducted on the date shown, the results of which are displayed below. All tests required by the specifications required for classification were performed at that time the product tested met all requirements. The Electrode was manufactured and supplied in accordance with the Quality System Program of National Standard Company, located in Stillwater, Oklahoma, U.S.A. This Quality System Program meets the requirements of ISO 9001:2008, AWS A5.20:2010, and CWB.

Operating Parameters	AWS/ASME Requirements	Data and Test Results
Electrode Size (in.)	--	.062"
Polarity	DCEP	DCEP
Shielding Gas (per AWS A5.32)	--	100%CO ₂
Voltage (volts)	--	28.3
Wire Feed Speed (in/min)	--	229.1
Travel Speed (in/min)	--	11.0
Current (amps)	--	254.1
Average heat input (kJ/in)	25-50	39.6
Contact tip to work distance (in.)	--	0.625"
Passes/Layers	--	14/7
Preheat Temp. °F	60°F min.	RT
Interpass Temp. °F	300+/-25	300+/-25

Test Assembly Material:	ASTM A36, A370/E23
Radiographic Test:	Acceptable
Fillet Weld Test:	N/A
Tensile Condition:	OD- 0.504" Aged at 482°F, up to 16 hr
Radiograph:	Pass

General Note:
Mechanical and/or Chemical testing were conducted in accordance with the following standard test procedure: ASTM A370/E23, ASTM E8. The attached results should not be assumed to be the expected results in a particular application. Results will differ depending on many factors, such as temperature, weld procedure, plate chemistry, welding method, and fabrication. It is advised to users to confirm by qualification testing the suitability of any welding before use in their applications.

Mechanical Properties of the Weld Deposit		
Tensile Strength (ksi)	70-95	85.7
Yield Strength,0.2% offset (ksi)	58 min	73.2
% Elongation	22 min	27
%ROA	N/A	69%
Average CVN impact properties ft·lbf @ -20°F	20 ft.lbf @ -20°F	46 ft.lbf @ -22°F

Chemical Composition of the Weld Deposit (Weight %)

Element	C%	Mn%	Si%	P%	S%	Cr%	Ni%	Mo%	V%	Al%	Cu%
AWS/ASME Requirements	0.12 Max	1.75 Max	0.90 Max	0.030 Max	0.030 Max	0.20 Max	0.5	0.30 Max	0.08 Max	-----	0.35 Max
Results	.043	1.47	.69	.008	.011	.052	.418	.008	.010	.001	.066

Diffusible Hydrogen Data:

AWS A4.3 Requirements (mL/100g) for Diffusible Hydrogen	8
Average Diffusible Hydrogen Result (mL/100g)	7.4

Sarang Muley

Sarang Muley, Process Engineer

Date 11/22/16