Silver-Glide™NS-115 CopperFree™Welding Wire

AWS ER70S-6

Silver-Glide[™] NS-115 CopperFree[™] Welding Wire is a mild steel solid filler wire containing a high combined total of manganese and silicon. The wire produces a smooth, uniform welding arc, which minimizes weld spatter and results in excellent bead appearance and high operator appeal.

The excellent operating characteristics of NS-115 appeal to users seeking better performance in their ER70S-6 applications.

Manufacturing Advantages

- All metal transfer modes of GMAW
- Robotic, mechanized, or semi-automatic welding
- Welding steel with medium to heavy mill scale, light rust, or thin oil
- Single and multi-pass weldments
- Applications requiring a minimum 70,000 psi tensile strength
- Compatible with variety of low-alloy steels and other similar base metals
- Superior crack resistance to enhance durability and reliability of welds
- Minimized contamination for cleaner welds

Welding Positions

All position welding is possible when using the correct shielding gas blends, welding process, and welding parameters.

Shielding Gas Blends

- 100% CO₂
- 75-95% Argon/Balance CO₂
- 95-98% Argon/Balance O₂
- Flow rate of 35-50 CFH



Applications

- Agricultural Equipment
- Auto Body
- General Fabrication
- Pipe Welding

Specifications

Meets or Exceeds:

- AWS A5.18/A5.18M: ER70S-6 H4, ER48S-6
- ASME SFA-5.18: ER70S-6
- AWS A5.17: EH11K
- CWB W48: B-G 49A 3 C1 S6
- ABS

Storage

Welding wire should be stored in a dry, enclosed environment and in its originally sealed package.



3602 North Perkins Road Stillwater, OK 74075 Customer Service: 1-800-777-1618 www.NSARC.com





Silver-Glide[™] NS-115 CopperFree[™] Welding Wire

AWS ER70S-6

Typical Mechanical Properties (as welded)

Certified As	TENSILE STRENGTH PSI	YIELD STRENGTH PSI	MINIMUM ELONGATION %	CVN IMPACT VALUES @ 20° F	
NS Plus -115	82,200	65,200	29	60 ft-lbf	
NS 115 CopperFree™	88,800	73,500	27	39 ft-lbf	
AWS MINIMUM	/0.000		22	20 ft-lbf	

Typical Wire Chemistry Percentages (as required per AWS)

Certified As	с	Mn	Si	Р	s	Cu	Ni	Cr	Мо	v
NS Plus [®] -115 Typ.	0.08	1.49	0.9	0.01	0.01	0.14	0.05	0.04	0.008	0.006
NS 115 CopperFree™ Typ.	0.09	1.52	0.91	0.011	0.011	0.07	0.06	0.06	0.01	0.01
AWS A5.18/A5.18M	0.06/0.15	1.40/1.85	0.80/1.15	0.025 (max.)	0.035 (max.)	0.50 (max.)	0.15 (max.)	0.15 (max.)	0.15 (max.)	0.03 (max.)
AWS A5.17/A5.17M	0.06/0.15	1.40/1.85	0.80/1.15	0.030 (max.)	0.030 (max.)	0.35(max.)				



3602 North Perkins Road Stillwater, OK 74075 Customer Service: 1-800-777-1618 www.NSARC.com



